

## Datablad SLA

	KS908C	Clear
Simulates	ABS	ABS/PMMA
Color	Brown	Transparent
Properties	Brown resin with properties similar to ABS plastic. For accurate and detailed parts. Good temperature and moisture resistance with good strength.	Transparent resin with properties similar to ABS/PMMA plastic. Superior clear, building parts with outstanding clarity and excellent accuracy.
Hardness	75-80	75-80
Flexural modulus Mpa	2650-2750	2650-2750
Tensile strength Mpa	25-30	25-30
Tensile modulus, Mpa	2150-2350	2150-2350
Flexural strength Mpa	60-75	60-75
Elongation at break %	12-20	12-20
Impact strength kj/m2	58-70	58-70
Density, g/cm3		
Heat deflection temp (HDT)	58-68	58-68
Glass transition temp (TG)	55-70	55-70